

PRODUCT NAME	RECOMMENDED SPRAY EQUIPMENT	BRAND & MODELS TESTED	PRESSURE SETTING	NEEDLE/TIP SIZE	THINNING ADJUSTMENTS	DISTANCE TO SUBSTRATE	ADDITIONAL NOTES
<p>NOTE: The following safety equipment is recommended when spraying textures: eye protection; dust and mist respirator; long sleeve shirt and full length pants; gloves and head covering.</p>							
Metallic Paints	HVLP GUN	Titan TS 40P	N/A	17/000	Add 20-40% water or GOLDEN Airbrush Medium	8-12"	Mica particles can be difficult to spray through finer tips. Strain paint mixtures through an automotive-style paper paint filter if clogging persists, or ideally, move up to the next larger sized tip. GOLDEN Airbrush Medium is recommended- either with or without water- as it helps improve flow, leveling and a reduction in surface defects such as fish-eyes.
		Vapor 19000	40 psi	1.4mm			
Metallic Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#1 Hole	Not required	18"	Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900).
		GRACO RTX 1500	High	White	Thin 10-15% with water		
		GRACO Mark V	1,050 PSI	537	Not required		
Soapstone Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#1 Hole	Not required	18"	Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	White	Thin 10-15% with water		
Adobe Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		
Fresco Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#1 Hole	Not required	18"	Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	White	Thin 10-15% with water		

PRODUCT NAME	RECOMMENDED SPRAY EQUIPMENT	BRAND & MODELS TESTED	PRESSURE SETTING	NEEDLE/TIP SIZE	THINNING ADJUSTMENTS	DISTANCE TO SUBSTRATE	ADDITIONAL NOTES
Stucco Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	NOTE: Stucco Texture may cause skin irritation, and this can be increased when airborne. BE SURE TO TAKE ALL PRECAUTIONS AND USE PROPER PERSONAL PROTECTION WHEN SPRAYING THIS PRODUCT. 'Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		
Cut Sandstone Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	NOTE: Cut Sandstone Texture may cause skin irritation, and this can be increased when airborne. BE SURE TO TAKE ALL PRECAUTIONS AND USE PROPER PERSONAL PROTECTION WHEN SPRAYING THIS PRODUCT. 'Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		
Weathered Granite Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	Best used through hopper instead of tube feed. Use of tube will require thinning with water or suitable medium and the Graco RTX 1500 was shown to be the ideal equipment compared to other models tested (such as the RTX 900). Use of tube will require thinning with water or suitable medium. Apply evenly and use tools to smooth before drying.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		
Glass Bead Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	Difficult to spray without severe bounceback of beads. WEAR FULL FACE SHIELD! Best to skim coat a layer of thick Proceed Texture and spray into wet layer. Keep pressure setting to a minimum and adjust distance to reduce bounce-back.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		
Glass Bead XL Texture	HOPPER GUN	Marshalltown Sharpshooter	40 psi	#2 Hole	Not required	18"	Difficult to spray without severe bounceback of beads. WEAR FULL FACE SHIELD! Best to skim coat a layer of thick Proceed Texture and spray into wet layer. Keep pressure setting to a minimum and adjust distance to reduce bounce-back.
		GRACO RTX 1500	High	Gray	Thin 10-15% with water		