

Sandstone Texture

Technical Data Sheet – Page 1 of 2

000D361

Description

Golden Paintworks® Sandstone is a light grey, tintable, acrylic texture with a sandy, slightly coarse and uniform, aggregate that can be left rough, or troweled smooth depending on the desired finish. When dry, it holds Glazes well, yet offers time to work a colored Glaze before it sets. Sandstone can be colored with paint up to 25% of its volume without affecting its working properties, or tinted with universal colorants. A wide variety of finishes, including faux concrete can be achieved.

Key Features

- Highly versatile for a range of unique finishing effects
- Thins easily for brush applications
- Tintable for a wide range of colors
- Easily over-glazed
- Water clean up
- VOC Compliant

Packaging

Available in short-filled Quart, Gallon and Five Gallon Containers.

Surface Preparation

Surface must be clean, dry and free of dirt, oil, wax and grease. Remove any loose, flaking or chalking paint from the surface. Do not apply to slick or glossy surfaces. Prime surface with an appropriate, high-quality, water base primer and allow to fully dry.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women.

Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as properly fitted respirator (NIOSH approved) and- proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Application

Sandstone can be easily tinted to one of our recommended colors or custom tint as desired. This product contains naturally occurring materials and may have some batch to batch variability in color.

- Stir contents before use.
- Apply at room/ surface temperatures between 50° F - 90° F.
- If tinting, mix thoroughly with a drill and paddle mixer or similar mixing apparatus. Note: this product does not mix reliably on a paint shaker.

- Trowel, Brush, Roller or Spray Apply.
- Allow a minimum of 1 to 4 hours drying time between coats.
- Test your technique on a practice board before applying to walls.
- For interior use.

Note: When applying with a Stainless Steel Trowel, this material may “metal mark” as it begins to dry.

Tools

Trowel: Use a trowel designed for decorative plaster applications.

Brush: Natural white or black bristle brush preferred.

Roller: Use a texture roller cover.

Spray application

Thin to adjust for proper atomization using up to 2 parts paint to 1 part water. NOTE: Sandstone Texture may cause skin irritation, and this can be increased when airborne. Be sure to take all precautions and use proper personal protection when spraying this product. A dust and mist respirator, long sleeves, gloves and head covering are recommended.

Spray equipment options:

Hopper Sprayer:

- Marshalltown SharpShooter® or equivalent
- #2 tip (4/16" / 6mm orifice); 40 PSI
- No reduction required, but may be reduced up to 30% to adjust application properties.

Pump/compressed air sprayers with reservoir:

- Best Recommendation: Graco® TexSpray RTX 1500 or equivalent
- “Gray” tip; “high” air volume setting
- Reduce 10% - 15% with water when using line feed from stationary hopper.

Coverage

Highly dependent on application technique and number of layers.
Approx. 80-180sq.ft./gal.

Dry Time

@ 50% RH, 77° F: Touch 1 hour. Recoat in 2-4 hours. Air movement and exchange will assist in proper drying. Cold weather & high humidity will slow down cure time.

Clean Up

Clean your skin and equipment immediately after use with soap and warm water. Consult with local authorities for methods of disposal.

Storage

Store in a cool/dry location @ temperatures between 40° F & 90° F. Do not allow material to freeze or be exposed to temperatures exceeding 120° F for extended periods.

Sandstone Texture

000D361

Technical Data Sheet – Page 2 Of 2

<u>Physical/Performance Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Weight per Gallon (in lbs)	Gardner Cup	9.59
Specific Gravity	Calculated	1.15
Typical Weight Solids	Calculated	66%
Typical Volume Solids	Calculated	60%
Consistency/Appearance	Visual Observation	White textural paste
pH (initial)	pH Meter	8.7 – 9.3
Viscosity	Brookfield RVT	20,000–40,000 cP (spindle 7, 100 rpms)
Odor	Subjective	Slight ammonia
Gloss/Sheen (85 degrees)	Glossmeter	< 4 (85 degrees)
Base Polymer	Known	100% Acrylic
Flash Point	Closed Cup	None (water based)
Freeze/Thaw Stability	Lab Test	Pass: 5 Cycles
Shelf Life	Lab Test	Expect 2 Years @ 77° F
Storage Conditions	Recommendation	Cool/Dry, Avoid Freezing/Heat
Application Temperature	Recommendation	50° F to 90° F (best results)
Paintability	Recommendation	Excellent @ 4 - 6 hrs. drying
Application Thinner	Recommendation	Thins with water
Clean Up	Recommendation	Warm, soapy water
Coverage Per Gallon	Recommendation	Highly dependent on application technique and substrate. Approx.50-150sq.ft./gal.

Environmental & Transportation Information

VOC: <50 g/l
Not RCRA Hazardous for disposal
Not Dangerous Goods for shipping via any mode

SEE SDS FOR ADDITIONAL INFORMATION

LIMITED WARRANTY

In the unlikely event of product failure, and determination by GOLDEN that product did not meet intended quality or published specifications, GOLDEN will, at its discretion, either replace the product or refund the purchase price as the customer's sole remedy. GOLDEN expressly disclaims liability for incidental and consequential damages, to the extent allowed by law.

TDS Number: TDSD361
Date of Issue: April 2019